

CCI NEOBOND EP

Solvent-free Epoxy Resin-based Thixotropic Bonding Agent

Description

CCI Neobond EP is a two-component solvent-free thixotropic epoxy resin bonding system for joining old concrete to new concrete and old concrete to old concrete.

Pack A: Resin (White), Pack B: Hardener (Black)

Domains of Application

It is mainly used to bond permanent freshly mixed concrete or mortar, glazed bricks, tiles, steel, or other structural material to old sound concrete. It is based on a 100% epoxy formulation and contains no solvents or water diluents. CCI Neobond EP is a time-tested dimensionally stable compound, which has been extensively used for structural bonding.

Advantages

- ✓ Provides a permanent bond.
- ✓ Cures in both dry and damp conditions
- ✓ Thixotropic-Can be applied on vertical and overhead surfaces without sagging.
- ✓ Can be used as bonding agent for mortars, renders, stone, steel, iron etc.
- ✓ Easy to mix and apply.
- ✓ Excellent adhesion to most building material

Standard Compliance

CCI Neobond EP conforms to ASTM C 881 Grade 3 Type II.

Indicative Characteristics

Appearance of cured film	Grey
Specific gravity at 27°C	1.3 ± 0.1
Solid content, % (w/w)	> 98
Mixing Ratio, Pack A: B (by weight)	2: 1
Pot life, minutes at 27°C, 100 g mass	> 45
Application Temperature, °C	5 to 40
Coverage (Theoretical)	0.3 kg to 0.8 kg/m ² per coat depending on surface profile

Initial cure at 27°C, for pedestrian traffic	After 24 hours
Slant-Shear bond strength at 14 days, N/mm ²	12 (minimum) or concrete failure
Compressive strength, 14 days, MPa	> 60

Domains of Application

It is mainly used to bond permanent freshly mixed concrete or mortar, glazed bricks, tiles, steel, or other structural material to old sound concrete. It is based on a 100% epoxy formulation and contains no solvents or water diluents. CCI Neobond EP is a time-tested dimensionally stable compound, which has been extensively used for structural bonding.

Method of Application

Surface Preparation

Surface should be clean, free from dirt, loose particles, oil, grease, or other foreign material. Deep contaminated concrete or metal should be thoroughly cleaned by wire brush. Ensure that the surface is not too wet during application of Bonding Agent.

Mixing

A suitable power-driven mixer/stirrer is recommended for uniform mixing of CCI Neobond EP. Stir the base and hardener separately. Add hardener into the base and stir well till a uniform color is achieved. Wait for 5 minutes for induction. Remix the mass again before applying. All packs are pre-weighed and ready for on-site mixing. Do not use a fraction of any pack. Always use whole packs for the best results.

Application

Apply a thin layer of CCI Neobond EP with brush or squeeze to the existing surface, working well into the substrate. Place fresh concrete/mortar while it is still tacky (2 to 5 hours). A second coat of CCI Neobond EP may be applied after the first thin layer of the applied CCI Neobond EP passes its tacky stage, prior to placing the freshly mixed concrete or mortar. Good concrete practice should be followed in placing, consolidation and curing of concrete. While application, the substrate temperature should be at least 5°C but not above 40°C.

Shelf Life & Storage

12 months from the date of manufacturing when stored in unopened, original sealed and dry condition at a temperature range from +5°C to 40°C.

Packaging

6 kg kit (Resin Part A – 4 kg, Hardener Part B – 2 kg).

Precautions

- ✓ Store the material at the 5°C to 40°C temperature range in a shaded cool place and keep it away from fire and any heated body. Clean all tools with Methyl Ethyl Ketone (MEK) or any standard solvent before polymerization starts.
- ✓ Mix only sufficient materials for immediate requirements. Leave the mixed material to stand for 5 to 8 minutes to enable entrapped air, if any, to escape from the mix and then use as quickly as possible.
- ✓ Thixotropy or anti sagging property is greatly influenced with surface temperature.

Safety

- ✓ Wear hand gloves, safety shoes and safety goggles while using and handling the product.
- ✓ In case eyes or mouth are affected, wash with plenty of clean water and seek medical treatment immediately.

Before use, refer to the Material Safety Data Sheet (MSDS). The MSDS is available on www.ccichemicals.in or contact us at info@ccichemicals.in.

Registered Office	Regional Office	Chennai Plant	Mumbai Plant
Office No. 210 Shah Heritage Commercial CHS Plot No. 9, Sector 48, Seawood Navi Mumbai – 400 706 Maharashtra, India Mobile: +91 93247 27785 E-mail: kashinath.bera@ccichemicals.in	'LAKSHMAN MANERE' Old No. 17/2, New No. 42/2, R Block 6 th Main Road, Anna Nagar West Chennai – 600 040 Tamilnadu, India Mobile: +91 98400 73183 E-mail: durai.murugan@ccichemicals.in	No. 1, Perumal Koil Street Azhinjivakkam Sriperumpudhur Thiruvallur – 602 105 Tamilnadu, India	Plot No. A-51 Taloja Industrial Area MIDC, Taloja Navi Mumbai – 410 208 Maharashtra, India